



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : A61L 15/28, D01D 5/253	A1	(11) International Publication Number: WO 97/23248 (43) International Publication Date: 3 July 1997 (03.07.97)												
<p>(21) International Application Number: PCT/US96/20309</p> <p>(22) International Filing Date: 20 December 1996 (20.12.96)</p> <p>(30) Priority Data: 08/577,570 22 December 1995 (22.12.95) US</p> <p>(71) Applicant: McNEIL-PPC, INC. [US/US]; Grandview Avenue, Skillman, NJ 08558 (US).</p> <p>(72) Inventors: NGUYEN, Hien; 256 Hickory Corner Road, East Windsor, NJ 08520 (US). MARTENS, Nicolas; Weberstrasse 13, D-Wuppertal (DE). GARBOLINO, Glenn; 16 Sycamore Avenue, Edison, NJ 08817 (US).</p> <p>(74) Agents: CIAMPORCERO, Audley, A., Jr. et al.; Johnson & Johnson, One Johnson & Johnson Plaza, New Brunswick, NJ 08933 (US).</p>	<p>(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).</p> <p>Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i></p>													
<p>(54) Title: IMPROVED ABSORBENT BODY</p> <div data-bbox="292 1144 1250 1596"> <table border="1"> <caption>Data points for Absorption vs. Multi-limbed Fiber Content</caption> <thead> <tr> <th>Multi-limbed Fiber Content (wt-%)</th> <th>Absorption (%)</th> </tr> </thead> <tbody> <tr> <td>0</td> <td>11.8</td> </tr> <tr> <td>25</td> <td>12.1</td> </tr> <tr> <td>50</td> <td>12.8</td> </tr> <tr> <td>75</td> <td>13.6</td> </tr> <tr> <td>95</td> <td>12.7</td> </tr> </tbody> </table> </div> <p>(57) Abstract</p> <p>An absorbent body formed of an absorbent web having a blend of multi-limbed regenerated cellulosic fibers and non-limbed cellulosic fibers has surprisingly improved specific absorption capacity. This absorbent body may be in the form of sanitary napkins, tampons, diapers, and adult incontinence devices.</p>			Multi-limbed Fiber Content (wt-%)	Absorption (%)	0	11.8	25	12.1	50	12.8	75	13.6	95	12.7
Multi-limbed Fiber Content (wt-%)	Absorption (%)													
0	11.8													
25	12.1													
50	12.8													
75	13.6													
95	12.7													

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

- 1 -

Improved Absorbent BodyField of the Invention

The present invention relates to an absorbent body
5 having improved absorption characteristics. The body
has a mixture of a staple fibers having a multi-limbed
cross-section having at least three limbs and non-limbed
fibers. The combination of fibers provides improved
specific absorption capacity over an absorbent body
10 formed of either the multi-limbed fibers alone or the
non-limbed fibers alone.

Background of the Invention

Absorbent bodies are limited in their absorbent or
15 absorption capacity. Thus, they cannot continue to
absorb fluids once their absorption capacity is reached.

Thus, researchers continue to search for improved
absorption characteristics in absorbent bodies.

One solution has been to employ superabsorbent
20 materials in absorbent bodies. These materials absorb
liquids and swell into a gel-like substance. While
these materials have been accepted for some uses in
absorbent articles, they have yet to achieve acceptance
for all uses.

25 Developments in cellulosic fiber technology have
helped increase the absorption capacities of absorbent
bodies based on these fibers. For example, Courtaulds
PLC, EP 0 301 874 B1 discloses that regenerated
cellulosic fibers which have a multi-limbed cross-
30 section also have increased absorbency. While this
technology is a welcomed improvement, researchers

- 2 -

continue to look for even more improvements in absorption capacity.

Therefore, what is needed is a fibrous absorbent body having improved absorption characteristics.

5

Summary of the Invention

We have found that improvements to the absorption capacity of absorbent bodies can be achieved by adding non-limbed cellulosic fibers to multi-limbed regenerated
10 cellulosic fibers having at least three limbs to form an absorbent body. These non-limbed cellulosic fibers generally provide a lower specific absorption capacity than the multi-limbed fibers. As used here in the specification and claims, the term "specific absorption
15 capacity" denotes the mass of fluid absorbed by a fibrous absorbent body per unit of mass of the absorbent body in a dry state. As used here in the specification and claims, the term "cellulosic fiber" means that the fiber contains or is derived from cellulose, e.g.,
20 natural fibers containing cellulose, such as cotton, and man-made fibers derived from cellulose, such as cellulose acetate.

What is unexpected is that the addition of the less absorbent, non-limbed fibers actually increases the
25 specific absorption capacity of absorbent bodies comprising the multi-limbed fibers. Thus, the fibers are added in an amount effective to increase the specific absorption capacity of the absorbent body. Preferably, the non-limbed fibers are present in an
30 amount to increase the specific absorption capacity of the absorbent body to about 105% of the specific

- 3 -

absorption capacity of a similar absorbent body of 100 wt-% multi-limbed fibers.

Brief Description of the Drawing

5 Fig. 1 illustrates a graphical representation of the data of Example 1.

 Fig. 2 illustrates a graphical representation of the data of Example 2.

10 Detailed Description of the Invention

 The present invention takes advantage of the increased absorbency of multi-limbed, regenerated cellulosic fibers and improves this absorbency by adding an effective, specific absorption capacity-improving
15 amount of non-limbed cellulosic fibers. Multi-limbed, regenerated cellulosic fibers have been commercially available for a number of years. These fibers are known to possess increased specific absorbency over non-limbed fibers. One commercial example of these fibers are the
20 Galaxy[™] viscose rayon fibers available from Courtaulds PLC, London, England. These fibers are described in detail in Courtaulds PLC, EP 0 301 874 B1, the disclosure of which is hereby incorporated by reference.

 These multi-limbed fibers are described as comprising a
25 solid filament of regenerated cellulosic material having a decitex of less than 5.0 and a multi-limbed cross-section, each limb having a length-to-width ratio of at least 2:1. The fibers are preferably staple length fibers having three or four limbs and a generally
30 symmetrical cross-sectional shape, e.g., Y-, X, H, or T-shaped. A preferred cross-sectional shape is Y-shaped having an angle between limbs of about 120°. Preferred

- 4 -

regenerated cellulosic material are viscose having a cellulose content of 5 to 12 wt-% and a caustic soda content of 4 to 10 wt-%. The fibers are preferably spun having a salt figure of 4.0 to 12.0. It is expected
5 that any multi-limbed commercial fiber or even other such fibers, not currently commercially available, would be useful in the practice of the present invention. It is merely required that the fibers lead to an absorbent body having a relatively high specific absorption
10 capacity which is increased by the addition of a less absorbent, non-limbed fiber to form a fibrous absorbent body.

The specific absorption capacity of a fibrous absorbent body including the multi-limbed, regenerated
15 cellulosic fibers described above is increased by adding an amount of non-limbed cellulosic fibers. A representative, non-limiting list of cellulosic fibers includes natural fibers such as cotton, wood pulp, jute, bagasse, silk, wool, and the like; and processed fibers
20 such as regenerated cellulose, cellulose acetate, cellulose nitrate, rayon, and the like. Preferably, the non-limbed cellulosic fibers are rayon or cotton, and more preferably, the fibers are rayon.

These non-limbed fibers are less absorbent, i.e.,
25 have a lower specific absorption capacity, than the multi-limbed, regenerated cellulosic fibers. However, adding an effective, specific absorption capacity-improving amount of non-limbed cellulosic fibers to the multi-limbed fibers surprisingly increases the specific
30 absorption capacity of the resulting absorbent body. This increase is preferably to at least about 102% of the specific absorption capacity of a similar absorbent

- 5 -

body made of the multi-limbed fibers alone. More preferably, the specific absorption capacity increases to at least about 105%.

We have found that adding an amount up to about 60 wt-% of the non-limbed cellulosic fibers can improve the specific absorption capacity of an absorbent body having the multi-limbed cellulosic fibers. Preferably, the non-limbed fibers are present at about 5 to about 50 wt-% of the absorbent body, and more preferably, at about 10 to about 30 wt-% of the absorbent body. Thus, preferred mixtures of fibers include about 1 to about 60 wt-% non-limbed fibers and about 99 to about 40 wt-% multi-limbed fibers; more preferred mixtures include about 5 to about 50 wt-% non-limbed fibers and about 95 to about 50 wt-% multi-limbed fibers; and most preferred mixtures include about 10 to about 30 wt-% non-limbed fibers and about 90 to about 70 wt-% multi-limbed fibers.

Additional fibers may also be included in the absorbent body. These additional fibers may include synthetic fibers such as polyesters, polyvinyl alcohols, polyolefins, polyamines, polyamides, polyacrylonitriles, and the like. These fibers may be included to add desirable characteristics to the absorbent body. For example, hydrophobic fibers may be used in outer surfaces of the body to reduce surface wetness and hydrophilic fibers may be used to increase the rate of fluid transport into and throughout the body.

The non-limbed and multi-limbed fibers are preferably blended to a substantially uniform mixture of fibers. These fiber blending operations are known to those of ordinary skill in the art. For example, the

- 6 -

fibers can be continuously metered into a saw-tooth opener. The blended fibers can be transported, e.g., by air through a conduit to a carding station to form a fibrous web. The fibrous web is preferably calendered to impart a minor amount of compression. This web can be further processed to form an absorbent body. For example, the web can be used to form an absorbent layer in a sanitary napkin, a diaper, or an adult incontinence device. In addition, the web can be formed into a tampon. In a tampon forming process, the web can be formed into a narrow, fibrous sliver and spirally wound to form a tampon blank. In addition, a liquid-permeable cover material can be wrapped around the tampon blank to substantially contain the fibrous absorbent portion of the tampon.

This tampon blank can then be pressed into a tampon. Such tampon blank compression is known to those of ordinary skill in the art. For example, the tampon can be formed according to Messing et al., U.S. Patent No. 3,422,496, or the commonly assigned, applications, Friese et al., U.S. Serial No. 07/596,454, and Schoelling, U.S. Serial No. 08/196,664, each of which is herein incorporated by reference.

25 Examples

The improved absorbent characteristics of the present invention can be further illustrated according to the following examples.

30 Example 1

A series of fibrous webs were formed by adding a measured amount of multi-limbed regenerated cellulosic

- 7 -

staple fibers (Galaxy™ rayon fibers, 3.3 denier, having a fiber length of about 30 mm, available from Courtaulds Fibres, London, England) and non-limbed regenerated cellulosic staple fibers (Danufil™ rayon fibers, 3.6 denier, having a fiber length of about 30 mm, available from Hoechst Kehlheim, Kehlheim, Germany) having the compositions identified in Table 1 below. For each web, the fibers were intimately mixed in and carded to form the fibrous web. This web was then calendered.

10

Table 1

15	Test Product	Sample Size	Avg. Wt.	Wt-% Galaxy	Wt-% Rayon
		(n)	(g)	(%)	(%)
20	Comp. Ex. A	5	2.5	100	0
	Comp. Ex. B	5	2.5	0	100
	Ex. C	5	2.5	75	25
	Ex. D	5	2.5	50	50
	Ex. E	5	2.5	25	75

The specific absorption capacity of these webs were then measured according to the following procedure:

The fibrous web was cut to provide a fibrous sample strip with a weight of 2.5 g. The sample strip was then saturated with water and left to drain the excess water for a period of five minutes. The sample strip was then weighed, and the amount of absorbed water was calculated.

The results of these measurements are displayed below in Table 2.

- 8 -

Table 2

5	Test Product	Absorpt.	Std. Dev.	Specific Absorpt.
		(g)	(g)	(g/g)
10	Comp. Ex. A	33.69	0.35	13.48
	Comp. Ex. B	29.24	0.73	11.69
	Ex. C	33.99	0.55	13.60
	Ex. D	32.31	0.77	12.92
	Ex. E	29.43	0.53	11.77

These data are also plotted in Fig. 1. It can be seen
that an absorbent web of 100% multi-limbed rayon fiber
has an absorption capacity which is greater than that of
an absorbent web of 100% non-limbed rayon fiber.
Unexpectedly, a blend of multi-limbed and up to about 30
wt-% non-limbed rayon fiber appears to increase the
specific absorption above that of an absorbent body of
100 wt-% of the more absorbent multi-limbed fibers.
Thus, these data illustrate that the incorporation of
non-limbed rayon fibers to the multi-limbed rayon fibers
provides a synergistic increase in the specific
absorption capacity of absorbent webs.

Example 2

A second series of fibrous webs was formed according
to the following procedure: The fiber components were
weighed using a component scale, mixed together in a
bale breaker and subsequently opened in a saw-tooth
opener. The resulting blend was carded to obtain the
fibrous web. The composition of these webs is
identified below in Table 3. The multi-limbed and non-
limbed fibers used in this Example 2 were the same as
used in Example 1 above. The cotton used in this

- 9 -

example was Cotton combers, supplied by Edward Hall, Stockport, England, having a fiber length of about 9mm to 13mm.

5

Table 3

	Test Product	Sample Size (n)	Avg. Wt. (g)	Wt-% Galaxy (%)	Wt-% Rayon (%)	Wt-% Cotton (%)
10	Comp. Ex. F	25	2.6	100	0	0
	Comp. Ex. G	25	2.6	0	100	0
	Ex. H	25	2.6	75	25	0
15	Ex. I	25	2.6	50	50	0
	Ex. J	25	2.6	25	75	0
	Ex. K	25	2.6	75	0	25

These webs were then used to manufacture compressed, radially-expanding, generally cylindrical tampons according to the process of the commonly assigned, applications to Friese et al., U.S. Serial No. 07/596,454, and Schoelling, U.S. Serial No. 08/196,664.

These tampons were conditioned at 21°C, 65% relative humidity for at least 24 hours and pre-weighed. The conditioned tampons were then tested according to the procedure for U.S. Food and Drug Administration Syngina tests, using an aqueous test solution as modified by adding the test fluid rapidly until tampon saturation and performing the procedure at about 20°C (room temperature). The results of these tests are illustrated below in Table 4.

- 10 -

Table 4

	Test Product	Syngina Absorpt. (g)	Std. Dev. (g)	Specific Syngina Absorp. (g/g)
5				
	Comp. Ex. F	12.50	0.26	4.81
	Comp. Ex. G	11.83	0.19	4.55
10	Ex. H	13.48	0.27	5.18
	Ex. I	12.73	0.17	4.90
	Ex. J	12.09	0.20	4.65
	Ex. K	13.12	0.24	4.86

15 Again, these data illustrate that the incorporation of non-limbed rayon fibers to the multi-limbed rayon fibers increases the specific absorption capacity of compressed absorbent tampons over that which would be expected by a mere addition of less absorbent fibers. These data are
20 also plotted in Fig. 2. This effect can be seen up to about a 50 to 60 wt-% add-on of non-limbed rayon or cotton fibers.

25 The specification and examples above are presented to aid in the complete and non-limiting understanding of the invention disclosed herein. Since many variations and embodiments of the invention can be made without departing from its spirit and scope, the invention resides in the claims hereinafter appended.

- 11 -

WHAT IS CLAIMED IS:

1. An absorbent body having improved absorption capacity comprising a mixture of about 40 to about 99
5 wt-% of regenerated cellulosic fibers having a multi-limbed cross-section having at least three limbs and about 60 to about 1 wt-% of non-limbed, cellulosic fibers.
- 10 2. The absorbent body of claim 1 wherein said multi-limbed regenerated cellulosic fibers comprise viscose rayon staple fibers.
3. The absorbent body of claim 1 wherein said non-
15 limbed cellulosic fibers comprise regenerated cellulosic fibers.
3. The absorbent body of claim 1 wherein said non-limbed cellulosic fibers comprise cotton fibers.
20
4. The absorbent body of claim 1 which comprises about 50 to about 95 wt-% of said multi-limbed fibers and about 50 to about 5 wt-% of said non-limbed fibers.
- 25 5. The absorbent body of claim 4 which comprises about 65 to about 85 wt-% of said multi-limbed fibers and about 35 to about 15 wt-% of said non-limbed fibers.
6. The absorbent body of claim 1 wherein said
30 mixture of fibers is compressed.

- 12 -

7. An absorbent body having improved absorption capacity comprising a mixture of multi-limbed regenerated cellulosic fibers having at least three limbs and an effective amount of non-limbed, cellulosic fibers to increase the specific absorption capacity of the absorbent body.

8. The absorbent body of claim 7 which comprises an effective amount of said non-limbed fibers to increase the specific absorption capacity to at least about 105% of the specific absorption capacity of a similar absorbent body of 100 wt-% multi-limbed fibers.

9. A method of increasing the absorption capacity of an absorbent body having multi-limbed regenerated cellulosic staple fibers comprising the steps of:

- combining an effective amount of non-limbed cellulosic staple fibers to increase the absorption capacity of the absorbent body with said multi-limbed regenerated cellulosic staple fibers, wherein said multi-limbed fibers have at least three limbs; and
- forming a web comprising a substantially intimate mixture of said combination of fibers.

10. The method of claim 9 further comprising compressing the web.


11. A method of forming a tampon comprising the steps of:

- 13 -


- combining about 1 to about 60 wt-% of non-limbed cellulosic staple fibers with about 99 to about 40 wt-% of multi-limbed regenerated cellulosic staple fibers, wherein said multi-limbed fibers have at least three limbs;
- forming said fibers into a tampon blank;
- compressing said tampon blank to form said tampon.

10 12. The method of claim 11 which further comprises covering said tampon blank with a cover material.

15 13. The method of claim 11 wherein the step of compressing the tampon blank comprises a fibrous core substantially surrounding the central axis, the core having a first average density, and a plurality of ribs which extend radially from the core, wherein each rib is separated from adjacent ribs where it is attached to the core and each rib contacts adjacent ribs proximate the
20 circumferential surface of the tampon.

FIG. 1

SUBSTITUTE SHEET (RULE 26)

FIG. 2

SUBSTITUTE SHEET (RULE 26)

INTERNATIONAL SEARCH REPORT

International Application No.

PL/US 96/20309

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 A61L15/28 D01D5/253

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 A61L D01D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P,X	EP 0 716 170 A (COURTAULDS FIBRES HOLDINGS LTD) 12 June 1996 see column 2, line 29 - line 51; claims ---	1-13
Y	EP 0 301 874 A (COURTAULDS PLC) 1 February 1989 cited in the application see the whole document ---	1-13
Y	GB 947 183 A (FARBWERKE HOECHST AG) 22 January 1964 see page 2, line 76 - line 107; claims ---	1-13
A	GB 2 085 304 A (KAO CORP) 28 April 1982 see claims ---	1-13

	-/--	



Further documents are listed in the continuation of best C.



Patent family members are listed in annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "A" document member of the same patent family

Date of the actual completion of the international search

23 April 1997

Date of making of the international search report

07.05.97

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

ESPINOSA, M

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/US 96/20309

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 4 129 679 A (WOODINGS CALVIN R) 12 December 1978 see claims -----	1-13

INTERNATIONAL SEARCH REPORT

nation on patent family members

International Application No

PL 1/US 96/20309

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0716170 A	12-06-96	NONE	
EP 0301874 A	01-02-89	GB 2208277 A	22-03-89
		AU 613934 B	15-08-91
		AU 2018488 A	02-02-89
		CA 1308224 A	06-10-92
		DE 3872088 A	23-07-92
		WO 8901062 A	09-02-89
		JP 1045811 A	20-02-89
		US 5458835 A	17-10-95
GB 947183 A		NONE	
GB 2085304 A	28-04-82	JP 1372038 C	07-04-87
		JP 57066754 A	23-04-82
		JP 61038696 B	30-08-86
		DE 3140450 A	09-06-82
		FR 2491759 A	16-04-82
		US 4362159 A	07-12-82
US 4129679 A	12-12-78	FR 2072510 A	24-09-71
		GB 1333047 A	10-10-73